


GreenGuard[®]

GG40-LG XPS Insulation Board

For use as general purpose insulation for roofing, wall and foundation applications requiring 40 psi minimum compressive strength



- Designed for high-load applications requiring insulation with minimum compressive strength of 40 psi
- Blowing agent blend GWP of less than 50
- R-value of 5.0 per inch of thickness
- Meets ASTM C578 Type VII requirements
- Excellent for high load floor and roofing systems, ice rinks, roadways as well as plaza and parking decks

GreenGuard®

GG40-LG XPS Insulation Board

Description

Kingspan GreenGuard® GG40-LG XPS Insulation Board is comprised of closed-cell extruded polystyrene (XPS) with a minimum compressive strength of 40 psi. It has high water resistance and R-value of 5.0 per inch of thickness. It has a formulation resulting in a GWP of less than 50. It is available in a square edge board or a drainage channel board.

Compliance

Where sold, compliant with state HFC regulations.

Intertek CCRR 1021;
 UL Listings- R11183;
 Miami-Dade County, FL;
 CCMC 12722-L.

Handling & Storage

When stored outdoors, XPS should be protected from exposure to direct sunlight using the original packaging or an opaque, light-colored tarp. XPS that has been unwrapped should be covered or rewrapped. XPS left exposed should be covered within 60 days to minimize UV damage. Once the exposed XPS is covered, the damage stops and is limited to the thin layer of cells on the surface that was exposed to the UV. XPS cells below the UV exposed surface layer are generally undamaged and the XPS overall performance remains intact.

WARNING: This product is combustible. A protective barrier or thermal barrier is required as specified in the appropriate building code. Protect it from exposure to open flame or other ignition sources during shipping, storage and installation.

Health & Safety

Kingspan GreenGuard® GG40-LG XPS Insulation Board is made of synthetic materials that are generally recognized as not providing a food source for insects, fungus, mold, or mildew. It should always be properly installed and stored. For detailed safe handling and safety information, refer to product SDS.

Kingspan GreenGuard GG40-LG XPS Insulation Board is free of HFC 134a.

This product should not be used as an exposed interior surface in buildings where people can be expected to be present. An approved fire protection barrier, such as ½" gypsum wallboard or equivalent, should be applied between this product and the interior of such buildings. Fire and building codes should be followed.

All assemblies should be evaluated for effectiveness and location of vapor retarders to avoid condensation and subsequent damage to structures (ASHRAE Handbook of Fundamentals). Since foam sheathings are non-structural, they must be installed over adequately braced framing in accordance with local building codes.

WARNING: Do not stand on or otherwise support your weight on this product unless it is fully supported by a load bearing surface.

Kingspan Insulation LLC

2100 Riveredge Parkway | Suite 175
 Atlanta | Georgia 30328

T: +1 (800) 241 4402 F: +1 (678) 589 7325

E: info@kingspaninsulation.us

www.kingspaninsulation.us

© Kingspan, the G Device and the Lion Device are Registered Trademarks of the Kingspan Group plc in the US, Canada and other countries. All rights reserved.

© GreenGuard is a Registered Trademark of the Kingspan Group plc in the US. All rights reserved.

kingspan-green-guard-gg40lg-product-data-sheet-en-us-ca-v2

| Product Data | | |
|---|------------------------------------|---------------------|
| Property | Test Method | Value |
| General | | |
| Nominal Thickness (in) | | 2, 3, 4 |
| Nominal Board Width (ft) | | 2/4 |
| Nominal Board Length (ft) | | 8 |
| Edge Profile | | Square Channeled |
| Property Type | ASTM C578 | VI |
| Compressive Strength, Min. (psi@10% deflection) | ASTM D1621 | 40 |
| Water Absorption, Max. (% by volume) | ASTM C272 | 0.3 |
| Water Vapor Permeance, Max (perm) | ASTM E96 (Desiccant Method) | 1.1 |
| Density, Min. (lb/ft³) | ASTM C303 | 1.8 |
| Service Temperature, Max. (°F) | | 165 |
| Thermal | | |
| Thermal Resistance, R-value¹ (°F·ft²·hr/Btu per in thick) | ASTM C518 (@75°F Mean Temperature) | 5.0 |
| Thermal Conductivity, k-value (Btu-in/hr·ft²·°F) | ASTM C518 (@75°F Mean Temperature) | 0.2 |
| Fire & Smoke | | |
| Flame Spread² Smoke Developed² | ASTM E84 / UL723 | 25 (Class A) 140 |

¹ Specimens are aged and tested in accordance with FTC Rule (16 CFR, Part 460) and ASTM C578.
 ² These numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by this material under actual fire conditions. All applicable building codes must be followed.

For more information on specific building product recommendations and installation guidelines, contact your Kingspan Insulation LLC representative.

For the most current product and compliance information go to www.kingspaninsulation.us

Kingspan Insulation LLC believes the information and recommendations herein to be accurate and reliable. However, since use conditions are not within its control, Kingspan Insulation LLC does not guarantee results from use of such products or other information herein and disclaims all liability from any resulting damage or loss. No warranty, express or implied, is given as to the merchantability, fitness for particular purpose, or otherwise with respect to the products referred to.

